

Technisches Datenblatt/ Technical Data Sheet

Fabricso Sheltera 240

Bezeichnung/ designation	Norm/ standard	Prüf- richtung/ test direction	Messwert/ test value	Einheit/ unit
Beschreibung/ description	unifarbiges Zeitgewebe mit einseitige transparente AC-Beschichtung/ uni tent fabric with transparent AC-coating on one side			
Bindung/ texture	Leinwand/ line weave			
Material/ material composition	(EU) No 1007/2011		100% Polyester	
Fertigbreite/ width	EN 1773		ca. 240 (approx. 94.5)	cm (inch)
Gewicht/ weight	EN 12127		ca. 230 (approx. 6.8)	g/m ² (oz/yd ²)
Dicke/ thickness	ISO 5084		ca. 0,25 (approx. 11.0)	mm (mil)
Zolltarifnummer/ HS-Code			59039099	
Dauerfaltverhalten/ crack resistance	ISO 7854-B		> 1.000.000	Knicke/ cracks
Wasserdruckbeständigkeit/ water pressure resistance	ISO 811		≥ 200 (≥2000)	mbar (mm)
Wasserabweisung/ water repellency	EN ISO 4920 (AATCC 22)	—	≥ 4-5 [of 5]	Note/ grade
Ölabweisung/ oil repellency	EN ISO 14419	—	≥ 4 [of 5]	Note/ grade
Wetterechtheit/ weather fastness	ISO 105-B04		≥ 6-7 [of 8]	Note/ grade
Lichtechntheit/ light fastness	ISO 105-B02		≥ 6-7 [of 8]	Note/ grade
Reibechtheit/ colour fastness to rubbing	ISO 105-X12	trocken/ dry	≥ 4-5 [of 5]	Note/ grade
		nass/ wet	≥ 4-5 [of 5]	Note/ grade
Chlorechtheit/ chlorine resistance	ISO 105-E03		≥ 4-5 [of 5]	Note/ grade
Migrationsechtheit/ Colour fastness to migration	ISO 105-X10 (in Abkantung/ in the style of)	helle Farben/ bright colors	≥ 4-5 [of 5]	Note/ grade
		dunkle Farben/ dark colors	≥ 3-4 [of 5]	Note/ grade
Hinweis zur Farbstoffmigration/ Note on dyestuff migration	Trotz der Verwendung neuester Herstellungsverfahren und Materialien gibt es äußere Einflüsse, die Auswirkung auf das sogenannte Migrationsverhalten (Farbstoffwanderung) von chemischen Substanzen haben können. Um eine Farbstoffmigration bei swela outguard zu vermeiden, sollte kein Direktkontakt zu anderen Textilien (vor allem PVC-Materialien) erfolgen. Dieser Hinweis ist bei der Weiterverarbeitung zu berücksichtigen. Despite the use of the latest manufacturing processes and materials, there are external influences that can have an effect on the so-called migration behaviour (dye migration) of chemical substances. In order to avoid dye migration at swela outguard, there should be no direct contact with other textiles (especially PVC materials). This information must be taken into account during further processing.			
Höchstzugkraft/ max. tensile strength	ISO 13934-1	Kette/ warp	≥ 1700	N
		Schuß/ weft	≥ 1550	N
Höchstzugkraftdehnung/ elongation	ISO 13934-1	Kette/ warp	≥ 32	%
		Schuß/ weft	≥ 22	%